

WOOD FILLER - [Coarse] Product No. **WCXXN** [Solvent based]

Solvent based wood filler course based on acrylic combination, mixed with modified coarse fillers, designed for the filling of the wood grain and wood defects surface irregularities holes and cracks.

USES

Ideal for Interior and Exterior use on all types of timber, e.g. natural, chipboard, plywood, etc..., especially for filling cracks, imperfections, and similar uneven surfaces of wood.

SPECIFICATIONS

Properties

- Application on Wood
- V. Good Adhesion
- V. Good Plasticity
- V. Good Hardness
- V. Good Coverage

Appearance	: Matt
Color	: Available in 19 different colors [please refer to Ritver Wood filler catalogue]
Specific gravity	: 1 Kg/lit [± 0.025].
Weight Solids	: Approx. 41% [± 2]
Flash point	: 7°C
Drying Time	
To Touch	: 20 min. At 25°C
Ready For Recoat	: 1.30 hrs. At 25°C
Hard Dry	: 4 hrs. At 25°C

SURFACE PREPARATION

All timber species must be fully aged with a moisture content of less than 15%. The Surface must be dry, clean and free from contaminations. Natural oil or gum must be removed by solvent cleaning.

To obtain optimum surface finish, sand the wood properly in the same direction of the wood grain, utilize sanding paper no. [120] to achieve smooth surface, as is adequate sanding and remove of dust prior to application of first coat of [WCXX] Wood Filler solvent based.

WOOD FILLER - [Coarse] Product No. **WCXXN** [Solvent based]

PRODUCT PREPARATION

Ready for use product, stir well before use. You can apply [WCXX] Wood Filler coarse, utilizing Swedish putty knife.

Dilution

Ready to use product.

For ease of application, you can dilute [WCXX] Wood filler coarse between 5-10% with NC thinner depending on the required application.

APPLICATION METHODS

Depends on the finishes required but in general an appropriate rate is between 800 g / sq. m. Apply [WCXX] Ritver wood filler coarse with putty knife or broad bladed knife, and spread materials evenly on the surface to smoothen, fill large holes in steps, allowing previous fill to set, followed by light sanding when dry until all imperfections is removed. [WCXX] Ritver wood filler coarse can be stained with Ritver stain range, exhibiting similar degree of absorption of the wood. A clear PU or NC coat can be applied after full drying process. Polyester base coat can be applied only after sealing the substrate.

CLEANING & CAUTION

Cleaning

Clean all tools and equipment immediately after use with [TC010] Tool Cleaner.

Caution

Do not use when humidity levels may cause surface condensation (maximum 85%), during rainy conditions or if temperatures are likely to fall below 5°C during application and drying. Protect from frost.

PACKING & STORAGE

Available in 0.5Kg, 1Kg.

Store in a cool and well ventilated place. Keep away from direct sunlight. Maximum 18 months in unopened container, stored in a cool and dry condition at 25°C.

SAFETY & FLAMMABLE

This material is nonflammable, but must not be exposed to direct sunshine.

Use in well ventilated areas. In case of contact with eyes, rinse immediately with plenty of sweet water and seek medical advice.

In case of contact with skin, wash with soap and water or a recognized skin cleanser.

Keep away from sources of ignition. No Smoking. Keep out of reach of children.