

STUCCO PUTTY Product No. PW2505

Ritver Stucco Putty is based on an acrylic copolymer formulated with pigments with good alkali resistant pigments. It is primarily used for filling surface irregularities, construction flaws, hairline surface cracks & indentations. The surface is rendered smooth and leveled with enough anchorage so as to apply a smooth layer of subsequent coats.

USE

Substrates: Concrete, plaster, masonry, gypsum, and wood works.
Area of Use: Interiors only.

SPECIFICATIONS

Properties

Finish	: Smooth & Buttery
Colour	: White
Specific gravity	: 1.8 ± 0.02
Solids (% by volume)	: 49 ± 1%
Diluent	: Sweet Water
Flash point	: Not Applicable
Spread Rate:	

While the spread rate is directly dependent on the surface profile and also the type of undulations it has, as a thumb rule **Ritver Stucco Putty** would cover 4 - 5 sq. meters per liter @ 100 microns and may be taken for cost calculations

Drying Time (30°C) : Set to touch: 1 – 2 hours.
: Ready for Recoat: app 6-8 hours.

Recommended DFT : **1 to 2 coats.** App 100 – 150 mic per coat.

SURFACE PREPARATION

A good surface preparation and following the method statement / recommended system procedure of Ritver is an ideal recommendation for the application of **Ritver Stucco Putty**.

For Plaster, Masonry & Concrete:

Achieve a good and clean surface by removing all contaminants by cleaning & drying. A laitance free surface should be achieved by good sweep blast or a wire brush.

Before applying the **Ritver Stucco Putty** apply one coat of **Ritver PVA Primer Sealer** and allow drying.

For Wood & Timber:

Achieve a good and clean surface by removing all contaminants by cleaning & drying treatment with **Ritver Wood Preservative compound** is advisable. Start off with a good coat of **Ritver Wood Primer** and allow to dry well.

Exclusions for successful application include perpetually wet surfaces and also large cavities on wooden surfaces.

STUCCO PUTTY Product No. PW2505

APPLICATION METHODS

Adequate ventilation is an ideal situation as it helps in drying and the good application itself. Avoid high humid conditions i.e., >95% when condensation is likely to interfere and also when the surface temperature is at least 3°C above dew point. One can add 5 to 10% of sweet water for ease of application depending on the suitability of application. One should apply with a putty knife or a broad bladed knife and spread it evenly on the surface to smoothen. After application light sanding may done to remove the imperfections.

TYPICAL PAINT SYSTEM

<p>Ritver Stucco Putty Recommended system to be applied as per surface preparation. (Suitable emulsion grades)</p> <p>■ Or as per Ritver technical advice</p>	<p>Ritver PVA Primer Sealer Ritver Stucco Putty Ritver Gold Emulsion</p>	<p>1 coat 2 coats 2 coats</p>
--	---	---------------------------------------

STORAGE & SHELF LIFE

Under dry and cool condition, storage stability can be sound up to 18 months in original sealed containers.

HANDLING

Disposal: As per the guidance and legislations of the local Authority e.g., by controlled landfill. In case of doubt, consult local authority. Do not empty into drains, sewers or other water courses.

Flash Point: Not applicable

SAFETY PRECAUTION

Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream. Other industrial practices are applicable.

Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapour or spray.

MSDS is available on request for the safe handling of this product.

FIRST AID

Eyes: In the event of accidental splashes, flush eyes with warm water immediately and obtain medical advice.

Skin: Wash skin thoroughly with soap and water or approved industrial cleaner. DO NOT USE solvent or thinners.

Inhalation: Remove to fresh air, loosen collar and keep patient rested.

Ingestion: In case of accidental ingestion DO NOT INDUCE VOMITING. Obtain immediate medical attention.

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RITVER Technical Service Department.