

CONCOAT EP250

Solvent Free Pigmented Epoxy Resin
Floor Coating with Hygienic properties

DESCRIPTION

CONCOAT EP250 is a high performance, two component, solvent free epoxy resin floor coating. The cured film forms a hard coating with excellent adhesion to concrete, granolithic screeds, and certain metal surfaces. It has hygienic properties due to the silver, iron incorporated into the painting formulas that makes it ideal with anti-bacterial properties. **CONCOAT EP250** cures to a glossy, impervious finish which can be easily cleaned. **CONCOAT EP250** is available in a wide range of colors and in clear grade.

CONCOAT EP250 complies with British standards BS 476, Part 7: 1971 and BS 5493 - 1971.

USE

CONCOAT EP250 is heavy duty traffic floor coating suitable for use in car parking areas, production assembly areas, workshops, dairies, soft drinks production and bottling plants, kitchens, showrooms and wet working areas.

CONCOAT EP250 provides a hard wearing, easily cleaned and attractive floor coatings in areas where high resistance to chemical attack is required.

CONCOAT EP250 is used as a top coat for concrete floors and as a finish coat for epoxy floor screeds to provide a more durable and easily cleaned surface where high impact is desirable.

ADVANTAGES

- High impact resistance
- Hard wearing – durable
- Low maintenance costs
- High abrasion resistance
- Provides hygienic – impervious finish
- Primerless
- High chemical resistance
- Applicable to apply on floor and walls



CONCOAT EP250

Solvent Free Pigmented Epoxy Resin
Floor Coating with Hygienic properties

SURFACE PREPARATION

All surfaces should be clean, dry and free from dust and other contaminants. Wet substrates should be used sponge dried to remove all surface water, then dried. Treat oil or grease contamination should be removed by degreaser followed by water or steam cleaning. **New concrete floors** should be at least 28 days and have a moisture content of less than 5%. Excessive laitance should be removed by mechanical method. Dust and other debris should be removed by vacuum cleaning.

Old concrete floors damaged areas or surface irregularities should be repaired by using EPOMORTAR FC two component fast curing epoxy mortar (Refer to TDS).

Steel surface should be grit blasted then clean by solvent and kept to dry.

Epoxy Screeds high spots or trowel marks should be rubbed down and remove dust and debris by vacuum cleaning then repair it by using EPOSCREED 10 three component epoxy screed (Refer to TDS.)

MIXING

The entire contents of the hardener container should be poured into the base container and the two materials mixed thoroughly for at least 3 minutes. Use of heavy duty slow speed power drill with a jiffy mixing blade. Mix the two components in the quantities supplied taking care to ensure hardener container is scraped clean. Do not add solvent thinners at any time.

APPLICATION

CONCOAT EP250 is recommended to apply in two coats. **CONCOAT EP250** can be applied to prepared surface using airless spray, brush or roller.

Ensure that the area is completely coated.

If anti-slip finishing is required, broad cast Silica Sand (0.25 – 1.00 mm, at 1 kg/m²) while first coat is wet. Applicator can use spiked shoes and confirm that all area completely covered. The second coat can be applied after 12 to 18 hours at 35 °C.

COVERAGE

4.5m² /litr at 250 microns (WFT) in two coats.

CLEANING

Tools and equipment can be cleaned immediately by using **THINNERCOAT 10** organic solvent.

PACKAGE

16 litr pack (including colored base and hardener)

CONCOAT EP250

Solvent Free Pigmented Epoxy Resin Floor
Coating with Hygienic properties

TECHNICAL PROPERTIES

Mixed Density	1.90 ± 0.05																						
Volume Solids (ASTM D 2823 – 91)	99% ± 1																						
Application Temperature	10°C to 45°C																						
Tack Free Time	2 hours at 35°C																						
Initial Hardness	20 hours at 35°C																						
Pot Life	35 minutes at 35°C																						
Full Cure	7 days at 35°C																						
Shore D Hardness ASTM D 2240	85																						
Pull – Off (On concrete) ASTM D 4541 – 85	2.5 N/mm ² (Concrete Faluire)																						
Flexural Strength BS 6319	36 N/mm ²																						
Tensile Strength ASTM D412	21 N/mm ²																						
Abrasion Resistance (ASTM D 1044-85, CS-17 Wheel 500gm load)	100 cycles 0.5-1.0 mg 500 cycles 3.5-4.5 mg 1000 cycles <9.0 mg																						
Water Absorbtion ASTM D 471	< 0.05%																						
Chemical Resistance: The following chemicals are spilled on applied samples for 7 days and found satisfy	<table style="width: 100%; border: none;"> <tr><td>Gasoline</td><td>Resistant</td></tr> <tr><td>Petrol</td><td>Resistant</td></tr> <tr><td>Diesel</td><td>Resistant</td></tr> <tr><td>Engine Oil</td><td>Resistant</td></tr> <tr><td>Kerosene</td><td>Resistant</td></tr> <tr><td>Skydrol</td><td>Resistant</td></tr> <tr><td>NaOH 20%</td><td>Resistant</td></tr> <tr><td>H₂ SO₄ 10%</td><td>Resistant</td></tr> <tr><td>HCl 10%</td><td>Resistant</td></tr> <tr><td>Acetic 5%</td><td>Resistant</td></tr> <tr><td>Brake Fluid</td><td>Resistant</td></tr> </table>	Gasoline	Resistant	Petrol	Resistant	Diesel	Resistant	Engine Oil	Resistant	Kerosene	Resistant	Skydrol	Resistant	NaOH 20%	Resistant	H ₂ SO ₄ 10%	Resistant	HCl 10%	Resistant	Acetic 5%	Resistant	Brake Fluid	Resistant
Gasoline	Resistant																						
Petrol	Resistant																						
Diesel	Resistant																						
Engine Oil	Resistant																						
Kerosene	Resistant																						
Skydrol	Resistant																						
NaOH 20%	Resistant																						
H ₂ SO ₄ 10%	Resistant																						
HCl 10%	Resistant																						
Acetic 5%	Resistant																						
Brake Fluid	Resistant																						

CONCOAT EP250

Solvent Free Pigmented Epoxy Resin Floor
Coating with Hygienic properties

STORAGE

Product should be stored at 25°C in dry conditions and keeping away from source of flame.

FLAMMABILITY

CONCOAT EP250 is nonflammable material.

THINERCOAT 10 is flammable, so do not expose to naked flames during application.

SHELF LIFE

18 months in tightly closed container.

HEALTH AND SAFETY

The application of material should be in good ventilation and avoid inhalation of the vapors. Use goggles and vinyl gloves. In case of contact with eyes, rinse immediately with plenty of clean water, do not use solvent and seek medical attention immediately. The product complies with environmental and occupational health & safety standards ISO 14001 and OHSAS 18001.