

## EPOMORTAR FC, EPOXY PUTTY Epoxy Mortar Fair Coat

### DESCRIPTION

**EPOMORTAR FC** is a two component solvent free epoxy mortar for filling pin holes, cracks and repairing irregularities of concrete. **EPOMORTAR FC** system has high bonding strength with concrete and steel structures. **EPOMORTAR FC** is an ideal material for repairing and bedding in a single operation with one material. It is used wherever a high degree of compressive strength, chemical resistance and excellent mechanical properties are required. This product is two pack reactive performance coatings for specific end such as floors under subcategory 10 of DM. VOC value for this product is less than 500g/l as per DM specs.

### USE

Typical applications include the following:

- cracks of concrete surface up to 3 mm width.
- Bedding Anchors.
- Floor repairing.
- Industrial kitchens and catering facilities.
- Electrical substations and plant rooms.
- Swimming pools and leisure facilities.
- Heavy duty workshops, garages and service facilities.
- Bottling plants and breweries.

### ADVANTAGES

- Smooth finish.
- Easy-on application.
- High ultimate compressive strength.
- Excellent chemical resistance.
- Impermeable when immersed in water.
- Primerless.
- Non-toxic.
- Excellent adhesion.
- Suitable for vertical and horizontal applications for interior and exterior locations.
- Available in a range of attractive colors.
- Low VOC.



### SURFACE PREPARATION

The surface should be dry (moisture < 5%) and any dust should be removed by industrial vacuum. In order to repair damaged area, cracks and honeycombs, laitance, dust and contaminants should be removed.

Prior to application, **EPOMORTAR FC** system should be stored under cover and protected from extremes of temperatures which may cause inconsistent workability and cure times for the mixed material. Ideally, at least 24 hours before mixing, **EPOMORTAR FC** system should be maintained at approximately 25°C. During

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RITVER Technical Service Department.

## EPOMORTAR FC, EPOXY PUTTY Epoxy Mortar Fair Coat

application in cold conditions, correct conditioning can help, but application should be halted if the ambient temperature is likely to fall below 10°C. The substrate or base slab is likely to be considerably colder than the surrounding air temperature. Pot life of the mixed material will be affected by ambient temperature. **New concrete floors** should be at least 28 days and have a moisture content of less than 5%. Excessive laitance should be removed by mechanical method. Dust and other debris should be removed by vacuum cleaning.

**Old concrete floors** damaged areas or surface irregularities should be repaired by using **EPOMORTAR FC** two component fast curing epoxy mortar (Refer to TDS).

**Steel surface** should be grit blasted then clean by solvent and kept to dry.

**Epoxy Screeds** high spots or trowel marks should be rubbed down and remove dust and debris by vacuum cleaning then repair it by using **EPOSCREED 10** three component epoxy screed (Refer to TDS.)

### MIXING

Part A (Grey) and part B (Off white) should be mixed together (mix ratio 1:1 by volume) in a suitable container until uniform color is obtained.

Use of heavy duty slow speed power drill with a jiffy mixing blade if there is separation on part (B). Mix the two components by using scraper or steel spatula.

### APPLICATION

Apply **EPOMORTAR FC** on the bed and repaired areas with a spatula, scraper or palette knife above the existing finished level.

Allow **EPOMORTAR FC** to dry to touch for approximately 4 - 6 hours depending on ambient temperature. Sand down the dried **EPOMORTAR FC** to achieve a flush overall surface.

### CURING

Good curing is essential for resin based materials to ensure specified performance. Installation using **EPOMORTAR FC** systems can be opened to foot traffic after approximately 24 hours at 25 °C. Complete cure is achieved after 72 hours at 25 °C.

### COVERAGE

Dependence on the irregularity of substrate.

### CLEANING

Tools and equipment can be cleaned immediately by using **THINNERCOAT 10** organic solvent.

### PACKAGE

10 kg pack (including part A and part B).

