

EPOXY PUTTY Product No. PS2011

Ritver Epoxy Putty is a High build stiff compound based on a selected epoxy resin and forms a two component product with a suitable catalyst. It forms a near rock hard product upon curing and is used to stop to fill cracks, indentations, blow holes, holes resulting out of construction flaws and damages due to mechanical abuse. By virtue of the epoxy resin composition it exhibits excellent resistance to mild acids, bases and other chemicals. It is very easy to apply and can accept top coats for cosmetic as well as protective nature.

USE

It is used to fill blow holes, construction flaws and other for severe industrial floors, car parking areas and heavy traffic with moderate load accompanied with good chemical and hot water resistance. It is recommended in animal rooms, poultry farms, food process units, beverages plants, and chemical industries. The product after curing can be abraded.

Substrates: Designed for medium to heavy industrial floors, car parking, animal houses, poultry farms, beverage plants.

Area of Use: Exterior and Interior

SPECIFICATION

Properties

Finish	: Smooth / Semi Gloss / Translucent
Colour	: White, Gray
Specific gravity	: Comp A: 1.80 ± 0.02, Comp B: 1.50 ± 0.02 (Mix SG 1.75 ± 0.02)
Mixed Solids (% by volume)	: Comp A: 80 ± 1%, Comp B: 93 ± 1% (Mix vol Sol: 83 ± 1%)
Mixing Ratio	: 2.5 : 1 (Component A: Component B wt / wt)
Pot Life	: App 1 – 1 ½ hour (at 30°C). Do not apply under direct sunlight
Diluent	: Not Applicable in general
Flash Point	: Not Applicable
Spread Rate:	The spread rate is directly dependant on the surface profile and the extend of damage and also the type of undulations it has.
Drying Time (30° C)	: Set to touch: 4 - 6 hours. : Ready for working: - 8 hours. : Full cure: app 7 days.
Recommended DFT	: Depends on the damaged area but unlimited by repeated coats.

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RITVER Technical Service Department.

EPOXY PUTTY Product No. PS2011

SURFACE PREPARATION

A good surface preparation and following the method statement / recommended system procedure of Ritver is an ideal recommendation for the application of **Ritver Epoxy Putty**.

For Concrete and related surfaces:

Ensure that the surface is sound. Remove laitance by thorough wire brushing, acid etching or sweep blasting. Blowholes and other defects should be filled with suitable filler. **Ritver Epoxy Floor Coating** or other top coats may be applied with an **Ritver Epoxy Primer** or a diluted version of the **Ritver Epoxy Floor Coating** in case of floor coating applications.

Exclusions for successful application include perpetually wet surfaces and also large cavities on metal and concrete surfaces.

APPLICATION METHODS

Adequate ventilation is an ideal situation as it helps in drying and the good application itself. Avoid high humid conditions i.e., >95% when condensation is likely to interfere and also when the surface temperature is at least 3°C above dew point.

Mix Part A and B in the recommended ratio thoroughly until uniform taking care that no excess air bubbles are formed.

Trowel or Spatula: This is the recommended method of application and the material can be sanded, if necessary. Press firmly in to indentations and level off whilst the putty is workable & pliable. This will minimize any further rubbing down that may be necessary. If rubbing down is required, it should commence 6-8 hours after application using a fine Grade 240 sand paper. Do not allow the If the stopper/putty is allowed to cure beyond 12 hours, it will become difficult to rubdown. The product is supplied as a two pack material and should be mixed thoroughly just prior to application.

One can use **Ritver Epoxy thinner** to clean the tools after the usage and is strongly recommended to do before drying.

Caution: Do not over thin it as there would be obvious shrinkage and difficulty in application.

EPOXY PUTTY Product No. PS2011

TYPICAL PAINT SYSTEM

<p>Ritver Epoxy Putty</p> <p>For use other mild steel surfaces</p> <p>Recommended system to be applied as per surface preparation, or as per Ritver technical advice.</p>	<p>Ritver Epoxy Primer Clear Ritver Epoxy Putty Ritver Epoxy Floor Coating (Top coat) Ritver Acrylic 2K Top coat</p>	<p>1 coat 2 coats 1 coat 1 coat</p>
--	--	--

STORAGE AND SHELF LIFE

Under dry and cool condition, Storage stability can be sound up to 18 months in original sealed containers. In no way should the component A & component B be mixed and kept.

HANDLING

Disposal: As per the guidance and legislations of the local Authority e.g., by controlled landfill. In case of doubt, consult local authority. Do not empty into drains, sewers or other water courses.

Flash Point: Not Applicable.

SAFETY PRECAUTION

Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream. Other industrial practices are applicable. Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapour or spray.

MSDS is available on request for the safe handling of this product.

FIRST AID

Eyes: In the event of accidental splashes, flush eyes with warm water immediately and obtain medical advice.

Skin: Wash skin thoroughly with soap and water or approved Industrial cleaner. DO NOT USE solvent or thinners.

Inhalation: Remove to fresh air, loosen collar and keep patient rested.

Ingestion: In case of accidental ingestion DO NOT INDUCE VOMITING. Obtain immediate medical attention.