



# BRONZE EMULSION Product No. PW2999

**Ritver BRONZE Emulsion** is an economical grade emulsion based on Acrylic copolymer resin with Titanium Dioxide and other light resistant pigments and fillers. It is particularly recommended as and indoor finish where it provides a very good value for money. It gives the surface a smooth and pleasing effect with good brush ability and recoat ability. It is resistant to algae and fungus attacks.

#### USE

Substrates: Concrete, plaster, masonry, gypsum.

Area of Use: Interiors only.

### **SPECIFICATIONS**

## **Properties**

Finish : Smooth & Matt

**Colour** : White + All shades as per Ritver shade card and custom made.

 $\begin{array}{lll} \textbf{Specific gravity} & : 1.48 \pm 0.02 \\ \textbf{Solids (% by volume)} & : 33 \pm 1\% \\ \textbf{Diluent} & : Sweet Water \\ \textbf{Flash point} & : Not Applicable \\ \end{array}$ 

Spread Rate:

While the spread rate is directly dependant on the surface profile and also the type of undulations it has, over spray and also the equipment the painter **Ritver Bronze Emulsion** it would cover app  $8.5~\text{m}^2$  / liter at 40 microns per coat.

**Drying Time (30° C)** : Set to touch: .5 – 1 hour depending on ambient temperature and air movement in the painting area

: Recoatable in 2 to 3 hours

**Recommended DFT** : **1 to 2 coats.** App 30 – 40 mic per coat.

### **SURFACE PREPARATION**

A good surface preparation and following the method statement / recommended system procedure of Ritver is an ideal recommendation for the application of **Ritver Bronze Emulsion.** 

# For Plaster, Masonry & Concrete:

Achieve a good and clean surface by removing all contaminants and loose particles by cleaning & drying. A laitance free surface should be achieved by good sweep blast or a wire brush. Water washing under pressure is recommended. Apply the **Ritver PVA Primer Sealer or Ritver Alkali Resistant Primer** and allow drying as per the data sheet and subject to one more coat for even coverage. Apply **Ritver Stucco Putty** evenly and allow drying and following it up with **Ritver Bronze Emulsion** for one or two coats.

### For Old and Painted surfaces:

In case of surfaces which are painted / or aged and is visible dusting, chalking or even friable ensure that all the loose material is removed by scrapping or metal brush. Apply a good coat **Ritver Fungicidal wash compound** and allow drying. Follow this by a regular coat or two of **Ritver PVA Primer Sealer or Ritver Alkali Resistant Primer** and continue as in the above case.

Date Revised: May 28, 2018

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please con tact RITVER Technical Service





2

# BRONZE EMULSION Product No. PW2999

### **APPLICATION METHODS**

Adequate ventilation is an ideal situation as it helps in drying and the good application itself. Avoid high humid conditions i.e., >95% when condensation is likely to interfere and also when the surface temperature is at least 3°C above dew point.

- **1. Dilution**: One can add 5 to 10% of sweet water for ease of application depending on the suitability of application.
- 2. Brush: It is in ideal recommendation especially to avoid runs and sags due to excess material.
- **Roller:** Apply an even coat spreading uniformly taking care to avoid runs.
- **4. Airless spray:** Use tip size around 0.018" to 0.020" and pressure around 150. 175 Kg/cm<sup>2</sup>.

### **TYPICAL PAINT SYSTEM**

Ritver Bronze Emulsion	Ritver PVA Primer Sealer Ritver Stucco Puttv	1 coat 2 coats
Recommended system to be applied as per surface preparation.	Ritver Bronze Emulsion	2 coats

• Or as per Ritver technical advice

### **STORAGE & SHELF LIFE**

Under dry and cool condition, storage stability can be sound up to  $18 \,$  months in original sealed containers.

### HANDLING

**Disposal**: As per the guidance and legislations of the local Authority e.g. by controlled landfill. In case of doubt, consult local authority. Do not empty into drains, sewers or other water courses.

Flash Point: Not applicable

### **SAFETY PRECAUTION**

Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream.

Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapour or spray.

MSDS is available on request for the safe handling of this product.

### **FIRST AID**

**Eyes**: In the event of accidental splashes, flush eyes with warm water immediately and obtain medical advice.

**Skin**: Wash skin thoroughly with soap and water or approved industrial cleaner. DO NOT USE solvent or thinners.

**Inhalation**: Remove to fresh air, loosen collar and keep patient rested.

**Ingestion**: In case of accidental ingestion DO NOT INDUCE VOMITING. Obtain immediate medical attention.

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please con tact RITVER Technical Service

Date Revised: May 28, 2018