

PU SEALER TIXOTHROPIC

Product No. **PB201-TIX**

[Superior Grade]

Superior Grade transparent two components Polyurethane sanding sealer formulated with condensed content combined with excellent wetting of the wood pore allows the sealing of any wood substrate. The product is fast drying with good leveling, sanding and antibacterial properties.

USES

Designed for use on all interior furniture and paneling, doors, windows, frames, veneer and casting. Can be used for open grain and closed grain finishes, depending on the viscosity and number of coats applied.

CHARACTERISTICS

Properties

- Superior Grade
- Very Good Sanding
- Very Good Plasticity
- Very Good Covering
- Good Adhesion
- Good Transparency

Color	: Transparent
Specific gravity	: 0.99 Kg/lit [± 0.025]
Weight Solids	: Approx. 48% [± 2]
Weight Solids blended	: Approx. 41% [± 2]
Viscosity @ 27/29°C	: 115 sec [± 5]
Flash point	: 21°C
Drying Time at 25°C	
Dust Free	: 15 min.
To Touch	: 25 min. at 25 μ DFT
Interval Coats	: 1 hr. 30 min.
To Sanding After	: 4 hrs. at 25 μ DFT
Deep Drying	: 24 hrs.

SURFACE PREPARATION

All timber species must be fully aged with a moisture content of less than 15%. The surface must be dry, clean and free from contaminations. Natural oil or gum must be removed by solvent cleaning. To obtain optimum surface finish, sand the wood properly in the same direction of the wood grain, utilize sanding paper no. [120]. Then and after sealer drying, utilize paper No.[220] to create smoothness to the substrate, then utilize paper No.[400] to achieve perfection of substrate till reaching between coats is essential, practice adequate sanding and remove dust prior to application of first coat. Control the compatibility of Stains eventually used

PU SEALER TIXOTHROPIC

Product No. **PB201-TIX**

[Superior Grade]

PRODUCT PREPARATION

CATALYST

by weight		by volume
50%	CP007 OR CP003 NY	50%
50%	CP002S	50%

Pot Life 3 hrs. @ 25°C

Stir product well with a flat paddle. Add the correct quantity of hardener and stir till homogeneous. Thin to required viscosity. For details of spray equipment contact Ritver Technical Services Department.

Dilution

Utilize PU Thinner depending on the application system used. In general 25 -30% thinner is added to achieve an application viscosity of 16-18 seconds Fc4. This is suitable for spraying.

For Curtain coater 25% Thinner is added to achieve an application viscosity of 30 second Fc4. In case of hot humidity climate add 5-10% [TP222] PU retardant thinner. In winter we suggest utilization of [TP290] for fast drying.

In Hot climate we suggest also utilization of [TP292] PU thinner to avoid bubbles and blooming.

APPLICATION METHODS

Depends on the finishes required but in general an appropriate rate is 120 gr / sq.m. The number of coats depends on the surface preparation the porosity of the substrate, and the finish required.

Following Treatments

By spray gun:

It is possible even to use airless and air-mix equipments. For details of spray equipment contact Ritver Technical Services Department.

By Curtain Coater:

It is recommended to control the viscosity during application by adding PU Thinner to balance the evaporation of solvents.

CLEANING

Clean all tools and equipment immediately after use with [TC010] Tool Cleaning.

PACKING & STORAGE

Available in 5Ltr, 25Ltr.

Store in a cool and well ventilated place. Keep away from direct sunlight. Maximum 18 months in unopened container, stored in a cool and dry condition at 25°C.

SAFETY & FLAMMABLE

This material is flammable and must not be exposed to naked flames.

Use only in well ventilated areas. In case of insufficient ventilation during application wear suitable respiratory equipment. Do not breathe vapor / spray. In case of contact with eyes, rinse immediately with plenty of sweet water and seek medical advice. In case of contact with skin, wash immediately with soap and water or a recognized skin cleanser. Keep away from sources of ignition. No Smoking. Keep out of reach of children.

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate and application, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RITVER Technical Service Department.

Date Revised: June 8, 2019